



THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:

Thomas Joseph Segatta et al

For: TIRE WITH APEX RUBBER BLEND

Serial No. 07/945,465

Filed: September 16, 1992

Docket No. 91221A

Art Unit: 1301

Examiner: A Johnstone

Express Mail mailing label number

EF644253185US

Date of Deposit December 12, 1994

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office t Addressee" service under 37 C.F.R. §1.10 on the date indicated above and is addressed to the Commissioner of Patents and Trademarks, Washington, D.C. 20231

Commissioner of Patents
and Trademarks
Washington, D.C. 20231

Signature

PRELIMINARY AMENDMENT

Dear Sir:

Prior to examination of the above-identified application, please amend the specification as follows:

IN THE SPECIFICATION:

C1
SubD1

1. (Twice Amended) A radial tire comprising a steel cord reinforced carcass ply and an apex of a composition comprised of, based on 100 parts by weight rubber, (A) about 80 to about 97 parts by weight of at least one rubber selected from the group consisting of natural rubber, synthetic cis 1,4-polyisoprene rubber, cis 1,4-polybutadiene rubber; and (B) about 3 to about 20 parts by weight of a trans 1,4-polybutadiene rubber have [at least a 65 percent trans 1,4-content] a 65 to about 90 percent trans 1,4-content, a 5 to about a 20 percent of a vinyl 1,2-content and a 2 to about a 15 percent cis 1,4-content and, in its uncured state, a first major melting point in the range of about 35°C to about 45°C and a second minor melting point in the range of about 55°C to about 65°C.